

# Radilon® S CV300 100 NT

## Radici Group High Performance Polymers - Polyamide 6

### General Information

#### Product Description

PA6 30% glass beads filled injection moulding grade. Natural colour.

Suitable for parts requiring good dimensional stability, reduced shrinkage and low warpage. It provides a good surface finish to moulded parts.

#### General

Filler / Reinforcement	• Glass Bead, 30% Filler by Weight
Features	• Good Dimensional Stability • Low Shrinkage • Good Surface Finish • Low Warpage
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-GB30

### Properties <sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.34	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.1	--	%	
Flow	1.1	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	8.0	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	2.2	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	566000	348000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	9430	5080	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	3.0	10	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	12	50	%	ISO 527-2/1A/50
Flexural Modulus <sup>2</sup>	537000	--	psi	ISO 178
Flexural Stress <sup>2</sup>	16700	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	1.7	--	ft·lb/in <sup>2</sup>	
73°F	1.9	2.6	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	14	--	ft·lb/in <sup>2</sup>	
73°F	17	19	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Bf
66 psi, Unannealed	338	--	°F	

## Radilon® S CV300 100 NT

### Radici Group High Performance Polymers - Polyamide 6

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	158	--	°F	ISO 75-2/Af
Vicat Softening Temperature	392	--	°F	ISO 306/B50
Melting Temperature <sup>3</sup>	428	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index Solution A	450	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index 0.08 in	1290	--	°F	IEC 60695-2-12

### Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	464 to 536	°F
Mold Temperature	176 to 194	°F
Injection Rate	Moderate-Fast	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 10°C/min