

Radilon® S RCP3010LW 322 BK

Radici Group High Performance Polymers - Polyamide 6

General Information

Product Description

PA6 30% glass fibre and mineral filler reinforced injection moulding grade. Heat stabilized. Black colour.

Suitable for parts requiring improved stiffness and dimensional stability, reduced shrinkage and low warpage.

General

Filler / Reinforcement	• Glass Fiber\Mineral, 30% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Good Dimensional Stability • Good Stiffness	• Heat Stabilized • Low Shrinkage	• Low Warpage
Uses	• Automotive Applications		
Agency Ratings	• EU 2011/65/EC		
RoHS Compliance	• RoHS Compliant		
Appearance	• Black		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA6-(GF+MX)30		

Properties ¹

Physical	Dry	Conditioned	Unit	Test Method
Density	1.38	--	g/cm ³	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.60	--	%	
Flow	0.40	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	7.5	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	2.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.13E+6	725000	psi	ISO 527-1/1A/1
Tensile Stress (Break)	15200	9430	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.7	10	%	ISO 527-2/1A/5
Flexural Modulus ²	1.04E+6	486000	psi	ISO 178
Flexural Stress ²	23200	13800	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	1.7	2.0	ft·lb/in ²	
73°F	1.9	2.9	ft·lb/in ²	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	17	19	ft·lb/in ²	
73°F	19	20	ft·lb/in ²	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Bf
66 psi, Unannealed	410	--	°F	

Radilon® S RCP3010LW 322 BK
Radici Group High Performance Polymers - Polyamide 6

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	374	--	°F	ISO 75-2/Af
Vicat Softening Temperature	401	--	°F	ISO 306/B50
Melting Temperature ³	428	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index Solution A	500	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index 0.08 in	1290	--	°F	IEC 60695-2-12

Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	464 to 536	°F
Mold Temperature	176 to 194	°F
Injection Rate	Moderate-Fast	

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ 10°C/min