

# Radilon® S USZ200 100 NT

## Radici Group High Performance Polymers - Polyamide 6

### General Information

#### Product Description

PA6 injection moulding grade. Toughened. Natural colour.

Suitable for parts requiring excellent impact resistance, even at low temperatures, and high flexibility.

#### General

Additive	• Impact Modifier
Features	• Good Impact Resistance • High Flexibility
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA6-HI

### Properties<sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.06	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.4	--	%	
Flow	1.5	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	7.9	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	2.0	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	232000	87000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	5800	2900	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	5.0	30	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	> 100	> 100	%	ISO 527-2/1A/50
Flexural Modulus <sup>2</sup>	203000	--	psi	ISO 178
Flexural Stress <sup>2</sup>	7980	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	38	--	ft·lb/in <sup>2</sup>	
73°F	45	--	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Bf
66 psi, Unannealed	275	--	°F	
Deflection Temperature Under Load				ISO 75-2/ Af
264 psi, Unannealed	122	--	°F	
Vicat Softening Temperature	302	--	°F	ISO 306/B50

## Radilon® S USZ200 100 NT

### Radici Group High Performance Polymers - Polyamide 6

Thermal	Dry	Conditioned	Unit	Test Method
Melting Temperature <sup>3</sup>	428	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index Solution A	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	< 1.2	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index 0.08 in	1200	--	°F	IEC 60695-2-12

### Processing Information

Injection	Dry Unit
Drying Temperature - Desiccant Dryer	176 °F
Drying Time - Desiccant Dryer	2.0 to 4.0 hr
Dew Point - Desiccant Dryer	< -4 °F
Suggested Max Moisture	0.15 %
Processing (Melt) Temp	482 to 536 °F
Mold Temperature	158 to 176 °F
Injection Rate	Moderate

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 10°C/min