

# Radilon® A RV500RKC 106 NT

## Radici Group High Performance Polymers - Polyamide 66

### General Information

#### Product Description

PA66 50% glass fiber reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring very high stiffness and mechanical resistance. Good resistance to hydrolysis. Product specifically intended for applications in civil and industrial water management sector. Suitable and approved for drinking water and foodstuff contact.

#### General

Filler / Reinforcement	• Glass Fiber, 50% Filler by Weight		
Additive	• Heat Stabilizer		
Features	• Food Contact Acceptable • Heat Stabilized	• High Stiffness • Hydrolysis Resistant	
Agency Ratings	• EU 2011/10/EC	• EU 2011/65/EC	• FDA 21 CFR 177.1500 Chapter 1
RoHS Compliance	• RoHS Compliant		
Appearance	• Natural Color		
Processing Method	• Injection Molding		
Resin ID (ISO 1043)	• PA66-GF50		

### Properties <sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.57	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	0.70	--	%	
Flow	0.20	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	4.0	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	1.1	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	2.41E+6	2.07E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	36300	27600	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	3.2	%	ISO 527-2/1A/5
Flexural Modulus <sup>2</sup>	2.20E+6	1.71E+6	psi	ISO 178
Flexural Stress <sup>2</sup>	55100	44200	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
73°F	8.1	12	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
73°F	52	57	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Af
264 psi, Unannealed	482	--	°F	
Vicat Softening Temperature	491	--	°F	ISO 306/B50
Melting Temperature <sup>3</sup>	500	--	°F	ISO 11357-3

## Radilon® A RV500RKC 106 NT

### Radici Group High Performance Polymers - Polyamide 66

Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
Comparative Tracking Index				IEC 60112
Solution A	600	--	V	
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index				IEC 60695-2-12
0.08 in	1290	--	°F	

### Processing Information

Injection	Dry	Unit
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 212	°F
Injection Rate	Moderate-Fast	

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 10°C/min