

# Radilon® A RV300RKC2 106 NT

## Radici Group High Performance Polymers - Polyamide 66

### General Information

#### Product Description

PA66 30% glass fiber reinforced injection moulding grade. Improved resistance to disinfectants. Heat stabilized. Drinking water and food contact.

Product with good resistance to hydrolysis and improved to disinfectants, specifically intended for use in applications in civil and industrial water management as well as applications, requiring high stiffness and good mechanical resistance.

#### General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Heat Stabilizer
Features	• Food Contact Acceptable • High Stiffness • Heat Stabilized • Hydrolysis Resistant
Uses	• Potable Water Applications
Agency Ratings	• EU 2011/65/EC • FDA 21 CFR 177.1500 Chapter 1
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-GF30

### Properties<sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.36	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.30	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	6.2	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	1.6	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	145000	1.09E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	27600	20300	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.8	5.0	%	ISO 527-2/1A/5
Flexural Modulus <sup>2</sup>	1.28E+6	943000	psi	ISO 178
Flexural Stress <sup>2</sup>	42800	31900	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	5.2	--	ft·lb/in <sup>2</sup>	
73°F	6.7	8.6	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	36	--	ft·lb/in <sup>2</sup>	
73°F	48	50	ft·lb/in <sup>2</sup>	

**Radilon® A RV300RKC2 106 NT**  
**Radici Group High Performance Polymers - Polyamide 66**

<b>Thermal</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Deflection Temperature Under Load 66 psi, Unannealed	491	--	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	473	--	°F	ISO 75-2/Af
Vicat Softening Temperature	482	--	°F	ISO 306/B50
Melting Temperature <sup>3</sup>	500	--	°F	ISO 11357-3
<b>Electrical</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity (500 V)	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity (500 V)	1.0E+13	1.0E+11	ohms·m	IEC 62631-3-1
<b>Flammability</b>	<b>Dry</b>	<b>Conditioned</b>	<b>Unit</b>	<b>Test Method</b>
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index 0.08 in	1290	--	°F	IEC 60695-2-12

**Processing Information**

<b>Injection</b>	<b>Dry</b>	<b>Unit</b>
Drying Temperature - Desiccant Dryer	176	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Dew Point - Desiccant Dryer	< -4	°F
Suggested Max Moisture	0.15	%
Processing (Melt) Temp	536 to 572	°F
Mold Temperature	176 to 212	°F
Injection Rate	Moderate-Fast	

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.079 in/min

<sup>3</sup> 10°C/min