

# Radilon® A RV350K 100 NT

## Radici Group High Performance Polymers - Polyamide 66

### General Information

#### Product Description

PA66 35% glass fiber reinforced injection moulding grade. Heat stabilized. Natural colour.

Suitable for parts requiring high stiffness, good mechanical resistance and good heat ageing properties retention.

#### General

Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Aging Resistant • Heat Stabilized • High Stiffness
Uses	• Automotive Applications
Agency Ratings	• EU 2011/65/EC
RoHS Compliance	• RoHS Compliant
Appearance	• Natural Color
Processing Method	• Injection Molding
Resin ID (ISO 1043)	• PA66-T GF35

### Properties <sup>1</sup>

Physical	Dry	Conditioned	Unit	Test Method
Density	1.40	--	g/cm <sup>3</sup>	ISO 1183
Molding Shrinkage <sup>2</sup>				ISO 294-4
Across Flow	1.0	--	%	
Flow	0.30	--	%	
Water Absorption				ISO 62
Saturation, 73°F, 0.0787 in	6.3	--	%	
Water Absorption				ISO 62
Equilibrium, 73°F, 0.0787 in, 50% RH	1.5	--	%	
Mechanical	Dry	Conditioned	Unit	Test Method
Tensile Modulus	1.60E+6	1.44E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	28300	18900	psi	ISO 527-2/1A/5
Tensile Strain (Break)	4.0	4.5	%	ISO 527-2/1A/5
Flexural Modulus <sup>3</sup>	1.42E+6	--	psi	ISO 178
Flexural Stress <sup>3</sup>	42800	--	psi	ISO 178
Impact	Dry	Conditioned	Unit	Test Method
Charpy Notched Impact Strength				ISO 179/1eA
-22°F	4.8	--	ft·lb/in <sup>2</sup>	
73°F	6.7	8.1	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength				ISO 179/1eU
-22°F	43	--	ft·lb/in <sup>2</sup>	
73°F	48	50	ft·lb/in <sup>2</sup>	
Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load				ISO 75-2/Bf
66 psi, Unannealed	482	--	°F	

## Radilon® A RV350K 100 NT

### Radici Group High Performance Polymers - Polyamide 66

Thermal	Dry	Conditioned	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	455	--	°F	ISO 75-2/Af
Vicat Softening Temperature	482	--	°F	ISO 306/B50
Melting Temperature <sup>4</sup>	500	--	°F	ISO 11357-3
Electrical	Dry	Conditioned	Unit	Test Method
Surface Resistivity <sup>5</sup>	1.0E+12	1.0E+10	ohms	IEC 62631-3-2
Volume Resistivity <sup>5</sup>	1.0E+15	1.0E+13	ohms·cm	IEC 62631-3-1
Comparative Tracking Index Solution A	600	--	V	IEC 60112
Flammability	Dry	Conditioned	Unit	Test Method
Burning Rate (0.118 in)	0.0	--	in/min	ISO 3795
Flame Rating (0.031 in)	HB	--		UL 94
Glow Wire Flammability Index 0.08 in	1290	--	°F	IEC 60695-2-12

### Processing Information

Injection	Dry Unit
Drying Temperature - Desiccant Dryer	176 °F
Drying Time - Desiccant Dryer	2.0 to 4.0 hr
Dew Point - Desiccant Dryer	< -4 °F
Suggested Max Moisture	0.15 %
Processing (Melt) Temp	536 to 572 °F
Mold Temperature	176 to 212 °F
Injection Rate	Moderate-Fast

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 300°C Melt Temperature/ 90°C Mold Temperature/ 60 MPa Cavity Pressure

<sup>3</sup> 0.079 in/min

<sup>4</sup> 10°C/min

<sup>5</sup> 500V