

DURANEX® 2002

Polyplastics - Polybutylene Terephthalate

General Information

Product Description

HB, Standard

Unfilled, Toughness

General

Features	• Good Toughness
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT<

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.31	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	8700	psi	ISO 527-2
Nominal Tensile Strain at Break	50	%	ISO 527-2
Flexural Modulus	381000	psi	ISO 178
Flexural Stress	13800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.6	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	158	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	6.1E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.1E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	5.0E+16	ohms·cm	IEC 60093
Electric Strength (0.118 in)	360	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	
Color Number	EF2001/ED3002		