

# DURANEX® 756HA

## Polyplastics - Polybutylene Terephthalate + PET

### General Information

#### Product Description

Better Surface Appearance, Higher Gloss, Flame Retardant

GF Reinforced, Low Warpage

#### General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Good Surface Finish • High Gloss • Low Warpage
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT+PET-(GF+TD)20FR(17)<

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.54	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	12600	psi	ISO 527-2
Tensile Strain (Break)	3.0	%	ISO 527-2
Flexural Modulus	776000	psi	ISO 178
Flexural Stress	19300	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.0	ft-lb/in <sup>2</sup>	ISO 179/1eA
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	356	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	2.8E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Electric Strength (0.118 in)	460	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	
Color Number	EF2001/ED3002/Colored		