

# DURANEX® 353RA

## Polyplastics - Polybutylene Terephthalate

### General Information

#### Product Description

Resin Adhesion Improved For Multiple Injection Molding

GF30% Reinforced, Hydrolysis Resistance

#### General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Good Adhesion • Hydrolysis Resistant
UL File Number	• E213445
Forms	• Pellets
Processing Method	• Injection Molding
Part Marking Code (ISO 11469)	• >PBT-GF30FR(17)<

### Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.68	g/cm <sup>3</sup>	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	20700	psi	ISO 527-2
Tensile Strain (Break)	2.1	%	ISO 527-2
Flexural Modulus	1.50E+6	psi	ISO 178
Flexural Stress	32100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	4.8	ft·lb/in <sup>2</sup>	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	387	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	1.1E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	3.9E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	1.0E+16	ohms·cm	IEC 60093
Electric Strength (0.118 in)	510	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94
Additional Information	Nominal Value	Unit	
Color Number	EF2001/ED3002		