

DURANEX® CN7005NN/BB

Polyplastics - Polybutylene Terephthalate

General Information

Product Description

Flame Retardant, Standard, UL Approved Regrind 50% Inclusive

GF5% Reinforced

General

Filler / Reinforcement	• Glass Fiber, 5.0% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Regrind and Blending Performance
UL File Number	• E213445
Forms	• Pellets, Reprocessed
Part Marking Code (ISO 11469)	• >PBT-GF5FR(17)<

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.46	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.20	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	10200	psi	ISO 527-2
Tensile Strain (Break)	3.7	%	ISO 527-2
Flexural Modulus	513000	psi	ISO 178
Flexural Stress	16800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	1.7	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	376	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	3.9E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	5.0E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	6.0E+16	ohms-cm	IEC 60093
Electric Strength (0.118 in)	430	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94