

DURANEX® CN7020NN/BB

Polyplastics - Polybutylene Terephthalate

General Information

Product Description

Flame Retardant, Standard, UL Approved Regrind 50% Inclusive

GF20% Reinforced

General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Flame Retardant
Features	• Flame Retardant • Regrind and Blending Performance
UL File Number	• E213445
Forms	• Pellets, Reprocessed
Part Marking Code (ISO 11469)	• >PBT-GF20FR(17)<

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.60	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.10	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	17700	psi	ISO 527-2
Tensile Strain (Break)	2.6	%	ISO 527-2
Flexural Modulus	1.06E+6	psi	ISO 178
Flexural Stress	26100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.6	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	95		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	406	°F	ISO 75-2/A
CLTE - Flow (73 to 131°F)	1.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+16	ohms·cm	IEC 60093
Electric Strength (0.118 in)	430	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94