

# CALIBRE™ 5201-8

## Trinseo - Polycarbonate Resin

### General Information

#### Product Description

CALIBRE™ 5201-8 polycarbonate resin is 20% glass reinforced containing mold release for optimal processing. This resin exhibits high modulus and excellent dimensional stability. CALIBRE 5201-8 resin is typically used in electrical market applications. CALIBRE 5201-8 resin has undergone biocompatibility testing based on ISO 10993 (Biological Evaluation of Medical Devices) and is suitable for use in approved medical applications.

#### Main Characteristics:

- Glass reinforced
- Ignition resistant
- Tested under ISO 10993

#### Applications:

- Electrical boxes
- Lighting components
- Electrical connectors
- Medical applications

#### General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Additive	• Mold Release
Features	<ul style="list-style-type: none"> <li>• Biocompatible</li> <li>• Ethylene Oxide Sterilizable</li> <li>• Flame Retardant</li> </ul> <ul style="list-style-type: none"> <li>• Good Dimensional Stability</li> <li>• Good Processability</li> <li>• Ignition Resistant</li> </ul> <ul style="list-style-type: none"> <li>• Radiation Sterilizable</li> </ul>
Uses	<ul style="list-style-type: none"> <li>• Electrical Housing</li> <li>• Electrical/Electronic Applications</li> </ul> <ul style="list-style-type: none"> <li>• Medical Devices</li> <li>• Medical/Healthcare Applications</li> </ul> <ul style="list-style-type: none"> <li>• Surgical Instruments</li> </ul>
Agency Ratings	• ISO 10993 <sup>1</sup>
Appearance	<ul style="list-style-type: none"> <li>• Colors Available</li> <li>• Opaque</li> </ul>
Forms	• Pellets
Processing Method	• Injection Molding

### Properties<sup>2</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.36		ASTM D792
Density	1.36	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	8.0	g/10 min	ISO 1133
Molding Shrinkage - Flow	2.0E-3 to 4.0E-3	in/in	ASTM D955
Molding Shrinkage - Flow	0.20 to 0.40	%	ISO 294-4
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>3</sup>	812000	psi	ASTM D638
Tensile Modulus	812000	psi	ISO 527-1/1
Tensile Strength <sup>4</sup> (Yield)	12000	psi	ASTM D638
Tensile Stress (Yield)	12000	psi	ISO 527-2/50
Tensile Strength <sup>4</sup> (Break)	12000	psi	ASTM D638
Tensile Stress (Break)	12000	psi	ISO 527-2/50
Tensile Elongation <sup>4</sup> (Yield)	4.0	%	ASTM D638

# CALIBRE™ 5201-8

## Trinseo - Polycarbonate Resin

Mechanical	Nominal Value	Unit	Test Method
Tensile Strain (Yield)	4.0	%	ISO 527-2/50
Tensile Elongation <sup>4</sup> (Break)	4.7	%	ASTM D638
Tensile Strain (Break)	4.7	%	ISO 527-2/50
Flexural Modulus	827000	psi	ASTM D790
Flexural Modulus <sup>5</sup>	812000	psi	ISO 178
Flexural Strength	21500	psi	ASTM D790
Flexural Stress <sup>5</sup>	21500	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.8	ft-lb/in	ASTM D256
Instrumented Dart Impact <sup>6</sup> (73°F, Total Energy)	410	in-lb	ASTM D3763
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	122		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	289	°F	ASTM D648
Deflection Temperature Under Load (66 psi, Annealed)	299	°F	ASTM D648
Deflection Temperature Under Load (66 psi, Annealed)	298	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed	280	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	280	°F	ISO 75-2/A
Deflection Temperature Under Load (264 psi, Annealed)	288	°F	ASTM D648
Deflection Temperature Under Load (264 psi, Annealed)	288	°F	ISO 75-2/A
Vicat Softening Temperature	311	°F	ASTM D1525 <sup>7</sup>
Vicat Softening Temperature	295	°F	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating <sup>8</sup>			UL 94
0.06 in		HB	
0.06 to 0.12 in		V-2	
0.10 to 0.13 in, White		V-1	
0.12 in		V-0	

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	248	°F
Drying Time	4.0	hr
Processing (Melt) Temp	554 to 608	°F
Mold Temperature	176 to 230	°F