

# Infino HN-3102GH

Lotte Chemical Corporation - Polycarbonate

## General Information

General			
Filler / Reinforcement	• Glass Fiber		
Properties <sup>1</sup>			
Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.26		ASTM D792
Density (Natural)	1.26	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	22	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (250°C/10.0 kg)	22	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	3.0E-3 to 6.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.30 to 0.60	%	
Flow : 0.0787 in	0.30 to 0.60	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	356000	psi	ASTM D638
Tensile Modulus	363000	psi	ISO 527-1/5
Tensile Strength <sup>2</sup> (Yield)	11400	psi	ASTM D638
Tensile Stress (Yield)	11600	psi	ISO 527-2/5
Tensile Strength <sup>2</sup> (Break)	11400	psi	ASTM D638
Tensile Stress (Break)	11600	psi	ISO 527-2/5
Tensile Elongation <sup>2</sup> (Break)	3.0	%	ASTM D638
Tensile Strain (Break)	3.0	%	ISO 527-2/5
Flexural Modulus <sup>3</sup>	498000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	508000	psi	ISO 178
Flexural Strength <sup>3</sup>	17100	psi	ASTM D790
Flexural Stress <sup>4</sup>	17400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	4.3	ft·lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	1.7	ft·lb/in	
73°F, 0.250 in	1.7	ft·lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	4.3	ft·lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	90		ASTM D785
Rockwell Hardness (R-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.252 in	280	°F	
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed, 0.157 in	280	°F	

# Infino HN-3102GH

## Lotte Chemical Corporation - Polycarbonate

Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	212	°F
Hot Air Dryer	1832	°F
Drying Time		
Desiccant Dryer	3.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	0.040	%
Rear Temperature	536 to 572	°F
Middle Temperature	536 to 572	°F
Front Temperature	536 to 572	°F
Nozzle Temperature	536	°F
Mold Temperature	140 to 212	°F
Injection Pressure	9960 to 21300	psi
Back Pressure	142 to 427	psi
Screw Speed	50 to 80	rpm

### Injection Notes

Hot Runner Temperature: 280°C

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 0.20 in/min

<sup>3</sup> 0.11 in/min

<sup>4</sup> 0.079 in/min

<sup>5</sup> 4mm