

# Infino UF-1050

Lotte Chemical Corporation - Polycarbonate

## General Information

### General

Material Status	• Commercial: Active		
Availability	• Africa & Middle East	• Europe	• North America
	• Asia Pacific	• Latin America	

## Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity (Natural)	1.19		ASTM D792
Density (Natural)	1.19	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ASTM D1238
Melt Mass-Flow Rate (MFR) (220°C/10.0 kg)	20	g/10 min	ISO 1133
Molding Shrinkage - Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage - Across Flow (0.126 in)	4.0E-3 to 7.0E-3	in/in	ASTM D955
Molding Shrinkage			ISO 294-4
Across Flow : 0.0787 in	0.40 to 0.70	%	
Flow : 0.0787 in	0.40 to 0.70	%	
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus <sup>2</sup>	299000	psi	ASTM D638
Tensile Modulus	305000	psi	ISO 527-1/50
Tensile Strength <sup>2</sup> (Yield)	9250	psi	ASTM D638
Tensile Stress (Yield)	9430	psi	ISO 527-2/50
Tensile Strength <sup>2</sup> (Break)	8530	psi	ASTM D638
Tensile Stress (Break)	8700	psi	ISO 527-2/50
Tensile Elongation <sup>2</sup> (Break)	85	%	ASTM D638
Tensile Strain (Break)	85	%	ISO 527-2/50
Flexural Modulus <sup>3</sup>	356000	psi	ASTM D790
Flexural Modulus <sup>4</sup>	348000	psi	ISO 178
Flexural Strength <sup>3</sup>	13500	psi	ASTM D790
Flexural Stress <sup>4</sup>	13100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength <sup>5</sup> (73°F)	26	ft-lb/in <sup>2</sup>	ISO 179/1eA
Notched Izod Impact			ASTM D256
73°F, 0.125 in	15	ft-lb/in	
73°F, 0.250 in	7.3	ft-lb/in	
Notched Izod Impact Strength <sup>5</sup> (73°F)	24	ft-lb/in <sup>2</sup>	ISO 180/1A
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	119		ASTM D785
Rockwell Hardness (R-Scale)	119		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
66 psi, Unannealed, 0.252 in	223	°F	
Deflection Temperature Under Load			ISO 75-2/B
66 psi, Unannealed, 0.157 in	221	°F	
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed, 0.252 in	207	°F	

# Infino UF-1050

## Lotte Chemical Corporation - Polycarbonate

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed, 0.157 in	198	°F	ISO 75-2/A
Vicat Softening Temperature	226	°F	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.04 in	V-0		
0.12 in	V-0		

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature		
Desiccant Dryer	176	°F
Hot Air Dryer	176	°F
Drying Time		
Desiccant Dryer	4.0	hr
Hot Air Dryer	4.0	hr
Suggested Max Moisture	< 0.050	%
Rear Temperature	482 to 518	°F
Middle Temperature	500 to 536	°F
Front Temperature	518 to 554	°F
Nozzle Temperature	518 to 554	°F
Mold Temperature	140 to 176	°F
Injection Pressure	14200	psi
Back Pressure	71.1 to 284	psi
Screw Speed	50 to 150	rpm

#### Injection Notes

Hot Runner Temperature: 270 to 290°C

#### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 in/min

<sup>3</sup> 0.11 in/min

<sup>4</sup> 0.079 in/min

<sup>5</sup> 4mm