

# Perlex R203 MOULDED SOLID GREEN 5-0577

## LyondellBasell Industries - Polycarbonate

### General Information

#### Product Description

Perlex R203 MOULDED SOLID GREEN 5-0577 is a Polycarbonate material. Features include: Good Flow, and UV Resistant.

#### General

Additive	• UV Stabilizer		
Features	• Good Flow	• UV Resistant	• UV Stabilized
Uses	• Automotive Applications	• Lighting Fixtures	

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.20	g/cm <sup>3</sup>	ISO 1183
Melt Mass-Flow Rate (MFR) (300°C/1.2 kg)	26	g/10 min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	341000	psi	ISO 527-1
Tensile Stress (Yield)	8700	psi	ISO 527-2
Tensile Strain (Break)	100	%	ISO 527-2
Flexural Modulus	334000	psi	ISO 178
Flexural Stress	13100	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (Area) (73°F)	19.0	ft·lb/in <sup>2</sup>	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	275	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed	257	°F	ISO 75-2/A
Vicat Softening Temperature	286	°F	ISO 306/B50
Flammability	Nominal Value	Unit	Test Method
Burning Rate			
0.0787 in	< 3.9	in/min	FMVSS 302
0.0787 in	< 3.9	in/min	ISO 3795
Flame Rating			UL 94
0.031 in		HB	
0.06 in		HB	
0.12 in		HB	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.04 in	1560	°F	
0.08 in	1560	°F	
0.12 in	1560	°F	