



TexRes PC FG10

TexCo Resin - Polycarbonate

General Information

General

Filler / Reinforcement • Glass Fiber, 10% Filler by Weight

Properties ¹

Physical	Nominal Value	Unit	Test Method
Specific Volume	79.1	in ³ /lb	ASTM D792
Melt Mass-Flow Rate (MFR)	12	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	12000	psi	ASTM D638
Tensile Elongation (Break)	8.0	%	ASTM D638
Flexural Modulus	530000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	2.6	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	270	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		Internal Method