



Polytrope TPP 1026EU 598F ANTHRACITE

LyondellBasell Industries - Thermoplastic Polyolefin Elastomer

General Information

Product Description

Extrusion TPO 13% Talc

General

Filler / Reinforcement	• Talc, 13% Filler by Weight
Processing Method	• Extrusion

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.00		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	4060	psi	ASTM D638
Flexural Modulus ³	290000	psi	ASTM D790

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min

³ 0.051 in/min