



Polytrope TPP 1817UVP-2599 GRYGRY

LyondellBasell Industries - Thermoplastic Polyolefin Elastomer

General Information

Product Description

TPO High Flow 17% Talc

General

Filler / Reinforcement	• Talc, 17% Filler by Weight
Features	• High Flow
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.02		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength ² (Yield)	2470	psi	ASTM D638
Flexural Modulus ³	239000	psi	ASTM D790

Notes

¹ Typical properties: these are not to be construed as specifications.

² 2.0 in/min

³ 0.051 in/min