

DURACON® HP270X

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

High Rigidity

High Flow

General

Features	• Copolymer	• High Flow	• High Rigidity
UL File Number	• E45034		
Forms	• Pellets		
Processing Method	• Injection Molding		
Part Marking Code (ISO 11469)	• >POM<		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	26	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	22	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	2.3	%	
Flow : 0.0787 in	2.0	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	442000	psi	ISO 527-1
Tensile Stress	10000	psi	ISO 527-2
Nominal Tensile Strain at Break	25	%	ISO 527-2
Flexural Modulus	406000	psi	ISO 178
Flexural Stress	14200	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ³	0.37		
vs. Steel - Dynamic ⁴	0.40		
Wear Factor			JIS K7218
140 psi, 59 ft/min ⁵	< 0.50	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
140 psi, 59 ft/min ⁶	40	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	90		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed	212	°F	
CLTE - Flow (73 to 131°F)	6.1E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.1E-5	in/in/°F	Internal Method

DURACON® HP270X

Polyplastics - Acetal (POM) Copolymer

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	IEC 60093
Volume Resistivity	1.0E+14	ohms·cm	IEC 60093
Electric Strength (0.118 in)	480	V/mil	IEC 60243-1
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	
Color Number	CF2001		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60x60x2mmt, Cavity Pressure 60 MPa

³ vs M90-44, 0.06 MPa, 15 cm/s

⁴ 0.98 MPa, 30 cm/s

⁵ vs C-Steel, Steel Side

⁶ vs C-Steel, Material Side