DURACON® TR-20LV

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description		
Low VOC		
Mineral Reinforced		

General		
Filler / Reinforcement	• Mineral	
Features	• Copolymer	• Low VOC
UL File Number	• E45034	
Forms	• Pellets	
Processing Method	• Injection Molding	
Part Marking Code (ISO 11469)	• >POM-TD15<	

Properties [1]

Physical	Nominal Value	Unit	Test Method
Density	1.53	g/cm³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	22	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	17	cm³/10min	ISO 1133
Molding Shrinkage [2]			ISO 294-4
Across Flow : 0.0787 in	1.7	%	
Flow : 0.0787 in	1.8	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.50	%	ISO 62
Mechanical	**Nominal Value**	**Unit**	**Test Method**
Tensile Modulus	616000	psi	ISO 527-1
Tensile Stress	7980	psi	ISO 527-2
Tensile Strain (Break)	8.0	%	ISO 527-2
Flexural Modulus	566000	psi	ISO 178
Flexural Stress	13100	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic [3]	0.40		
vs. Steel - Dynamic [4]	0.50		
Wear Factor			JIS K7218
71 psi, 59 ft/min [5]	5.0	10^-10 in³·min/ft·lb·hr	
8.7 psi, 30 ft/min [6]	250	10^-10 in³·min/ft·lb·hr	
71 psi, 59 ft/min [7]	1500	10^-10 in³·min/ft·lb·hr	
8.7 psi, 30 ft/min [8]	4500	10^-10 in³·min/ft·lb·hr	
Impact	**Nominal Value**	**Unit**	**Test Method**
Charpy Notched Impact Strength (73°F)	1.4	ft·lb/in²	ISO 179/1eA
Hardness	**Nominal Value**	**Unit**	**Test Method**
Rockwell Hardness (M-Scale)	75		ISO 2039-2

DURACON® TR-20LV

Polyplastics - Acetal (POM) Copolymer

Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed	253	°F	
CLTE - Flow (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	4.4E-5	in/in/°F	Internal Method
Flammability	**Nominal Value**	**Unit**	**Test Method**
Flame Rating	HB		UL 94
Additional Information	**Nominal Value**	**Unit**	
Color Number	CF2001		

Notes

[1] Typical properties: these are not to be construed as specifications.

[2] 60×60×2mmt, Cavity Pressure 60 MPa

[3] vs M90-44, 0.06 MPa, 15 cm/s

[4] 0.49 MPa, 30 cm/s

[5] vs C-Steel, Steel Side

[6] vs M90-44, Material Side

[7] vs C-Steel, Material Side

[8] vs M90-44, M90-44 Side