

DURACON® SL-20

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

Special

Silicon oil concentrate

General

Additive	• Silicone Lubricant
Features	• Copolymer • Lubricated
Forms	• Pellets
Part Marking Code (ISO 11469)	• >POM<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Water Absorption (24 hr, 73°F, 0.0394 in)	0.70	%	ISO 62
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	75		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (73 to 131°F)	7.2E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	7.2E-5	in/in/°F	Internal Method
Additional Information	Nominal Value	Unit	
Color Number	CF2001		