



DURACON® LU-02LV

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

Low VOC

Low Gloss, Weather Resistance

General

Features	<ul style="list-style-type: none"> Copolymer Good Weather Resistance 	<ul style="list-style-type: none"> Low Gloss Low VOC
Forms	<ul style="list-style-type: none"> Pellets 	
Processing Method	<ul style="list-style-type: none"> Injection Molding 	
Part Marking Code (ISO 11469)	<ul style="list-style-type: none"> >POM< 	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.39	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	19	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	18	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	2.1	%	
Flow : 0.0787 in	2.2	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.50	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	326000	psi	ISO 527-1
Tensile Stress	7830	psi	ISO 527-2
Nominal Tensile Strain at Break	20	%	ISO 527-2
Flexural Modulus	305000	psi	ISO 178
Flexural Stress	10400	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ³	0.37		
vs. Steel - Dynamic ⁴	0.80		
Wear Factor			JIS K7218
71 psi, 59 ft/min ⁵	< 0.50	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
71 psi, 59 ft/min ⁶	300	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
8.7 psi, 30 ft/min ⁷	740	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
8.7 psi, 30 ft/min ⁸	2500	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.6	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ISO 2039-2

DURACON® LU-02LV

Polyplastics - Acetal (POM) Copolymer

Thermal	Nominal Value	Unit	Test Method
CLTE - Flow (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	5.0E+15	ohms	IEC 60093
Volume Resistivity	7.0E+13	ohms·cm	IEC 60093
Additional Information	Nominal Value	Unit	
Color Number	CF2001		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60x60x2mmt, Cavity Pressure 60 MPa

³ vs M90-44, 0.06 MPa, 15 cm/s

⁴ 0.49 MPa, 30 cm/s

⁵ vs C-Steel, Steel Side

⁶ vs C-Steel, Material Side

⁷ vs M90-44, Material Side

⁸ vs M90-44, M90-44 Side