

DURACON® M90LV

Polyplastics - Acetal (POM) Copolymer

General Information

Product Description

Low VOC

Standard

General

Features	• Copolymer	• Low VOC
UL File Number	• E45034	
Forms	• Pellets	
Processing Method	• Injection Molding	
Part Marking Code (ISO 11469)	• >POM<	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.41	g/cm ³	ISO 1183
Melt Mass-Flow Rate (MFR) (190°C/2.16 kg)	9.0	g/10 min	ISO 1133
Melt Volume-Flow Rate (MVR) (190°C/2.16 kg)	8.0	cm ³ /10min	ISO 1133
Molding Shrinkage ²			ISO 294-4
Across Flow : 0.0787 in	2.3	%	
Flow : 0.0787 in	2.4	%	
Water Absorption (24 hr, 73°F, 0.0394 in)	0.60	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	383000	psi	ISO 527-1
Tensile Stress	8700	psi	ISO 527-2
Nominal Tensile Strain at Break	35	%	ISO 527-2
Flexural Modulus	341000	psi	ISO 178
Flexural Stress	12000	psi	ISO 178
Coefficient of Friction			JIS K7218
Dynamic ³	0.37		
vs. Steel - Dynamic ⁴	0.47		
Wear Factor			JIS K7218
71 psi, 59 ft/min ⁵	< 0.50	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
71 psi, 59 ft/min ⁶	74	10 ⁻¹⁰ in ³ ·min/ft·lb·hr	
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	3.3	ft·lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	80		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ISO 75-2/A
264 psi, Unannealed	199	°F	
CLTE - Flow (73 to 131°F)	6.7E-5	in/in/°F	Internal Method
CLTE - Transverse (73 to 131°F)	6.7E-5	in/in/°F	Internal Method

DURACON® M90LV

Polyplastics - Acetal (POM) Copolymer

Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	3.0E+16	ohms	IEC 60093
Volume Resistivity	3.0E+14	ohms·cm	IEC 60093
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		UL 94
Additional Information	Nominal Value	Unit	
Color Number	CF2001/CD3069		

Notes

¹ Typical properties: these are not to be construed as specifications.

² 60x60x2mmt, Cavity Pressure 60 MPa

³ vs M90-44, 0.06 MPa, 15 cm/s

⁴ 0.49 MPa, 30 cm/s

⁵ vs C-Steel, Steel Side

⁶ vs C-Steel, Material Side