



# Hostacom FPP35GFC LM CS1BWN15035

## LyondellBasell Industries - Polypropylene Homopolymer

### General Information

#### Product Description

35 % glass fiber reinforced PP-Homopolymer, long term heat stabilized. Former name: Polyfort FPP 35 GFC LM CS1

#### General

Filler / Reinforcement	• Glass Fiber, 35% Filler by Weight
Additive	• Copper Stabilizer
Features	• Chemically Coupled • Homopolymer • Copper Contact Stabilized • Laser Markable
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.16	g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	5.0	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.10E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	13100	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	3.8	ft-lb/in <sup>2</sup>	
73°F	4.3	ft-lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	21	ft-lb/in <sup>2</sup>	
73°F	23	ft-lb/in <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	318	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	293	°F	ISO 75-2/Af
Ball Pressure Test (293°F)	Pass		IEC 60695-10-2
Flammability	Nominal Value	Unit	Test Method
Burning Rate			
0.0787 in	2.4	in/min	ISO 3795
0.0787 in	2.4	in/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in	HB		
0.12 in	HB		
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in	1380	°F	
0.12 in	1380	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in	1430	°F	
0.12 in	1430	°F	

**Hostacom FPP35GFC LM CS1BWN15035**  
**LyondellBasell Industries - Polypropylene Homopolymer**

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F
Injection Rate	Moderate-Fast	

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.