

Hostacom PF062-3C HI BLK

LyondellBasell Industries - Polypropylene

General Information

Product Description

Hostacom PF062-3C HI BLK high melt flow, 5,200 MPa flexural modulus, precolored, chemically coupled, 30% glass fiber-reinforced polypropylene homopolymer has good impact strength, high stiffness and very good moldfilling capability.

General

Uses	• Automotive Applications	• Automotive Exterior Parts	• Automotive Under the Hood
Processing Method	• Injection Molding		

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.12		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	20	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	13100	psi	ASTM D638
Flexural Modulus	754000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.6	ft·lb/in	ASTM D256