

Polyflam RIPP 4000 OSD SF GRY64540

LyondellBasell Industries - Polypropylene Copolymer

General Information

Product Description

Flame-retardant PP-Copolymer, halogenfree, optimized smoke density

General

Additive	• Flame Retardant
Features	• Copolymer
	• Good Processability
Processing Method	• Flame Retardant
	• Halogen Free
	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	6.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	276000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	2470	psi	ISO 527-2/1A/50
Tensile Stress (Break)	1890	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	2.5	%	ISO 527-2/1A/50
Nominal Tensile Strain at Break	18	%	ISO 527-2/1A/50
Flexural Modulus ²	305000	psi	ISO 178
Flexural Stress ² (3.5% Strain)	4060	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	0.76	ft·lb/in ²	
73°F	1.1	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	6.7	ft·lb/in ²	
73°F	33	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	226	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed	138	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	172	°F	ISO 306/B50
--	297	°F	ISO 306/A50
Electrical	Nominal Value	Unit	Test Method
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ³			
0.0787 in	0.0	in/min	ISO 3795
0.0787 in	0.0	in/min	FMVSS 302

Polyflam RIPP 4000 OSD SF GRY64540
LyondellBasell Industries - Polypropylene Copolymer

Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.030 in		V-0	
0.06 in		V-0	
0.12 in		V-0	
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in	1760	°F	
0.06 in	1760	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in	1340	°F	
0.06 in	1340	°F	
0.12 in	1340	°F	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	356	°F
Middle Temperature	392	°F
Front Temperature	410	°F
Nozzle Temperature	428	°F
Processing (Melt) Temp	356 to 428	°F
Mold Temperature	104 to 176	°F
Injection Pressure	11600 to 17400	psi
Injection Rate	Slow-Moderate	
Holding Pressure	5800 to 13100	psi
Back Pressure	725 to 1450	psi
Screw Speed	< 709	in/min
Cushion	< 0.197	in

Notes

¹ Typical properties: these are not to be construed as specifications.

² 0.079 in/min

³ Self-Extinguishing