

# Polyflam RPP 2000S R9016 WHI87235

LyondellBasell Industries - Polypropylene Homopolymer

## General Information

### Product Description

Flame retardant polypropylene homopolymer compound, UV stabilized for outdoor applications (i.e. stadium seats), free of halogens

### General

Additive	<ul style="list-style-type: none"> <li>Flame Retardant</li> <li>UV Stabilizer</li> </ul>
Features	<ul style="list-style-type: none"> <li>Flame Retardant</li> <li>Halogen Free</li> <li>Homopolymer</li> <li>UV Stabilized</li> </ul>
Uses	<ul style="list-style-type: none"> <li>Outdoor Applications</li> <li>Seats</li> </ul>
Processing Method	<ul style="list-style-type: none"> <li>Injection Molding</li> </ul>
Resin ID	<ul style="list-style-type: none"> <li>PP FR(53)</li> </ul>

## Properties<sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	0.910	g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	7.0	cm <sup>3</sup> /10min	ISO 1133
Water Absorption (Equilibrium, 73°F, 50% RH)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	160000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	4640	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	11	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.4	ft-lb/in <sup>2</sup>	ISO 179/1eA
Charpy Unnotched Impact Strength (73°F)	No Break		ISO 179/1eU
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	201	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	120	°F	ISO 75-2/ Af
Vicat Softening Temperature			
--	194	°F	ISO 306/B50
--	304	°F	ISO 306/A120
Ball Pressure Test (284°F)	Pass		IEC 60695-10-2
RTI Elec			UL 746B
0.030 in	149	°F	
0.06 in	149	°F	
0.12 in	149	°F	
RTI Imp			UL 746B
0.030 in	149	°F	
0.06 in	149	°F	
0.12 in	149	°F	
RTI Str			UL 746B
0.030 in	149	°F	
0.06 in	149	°F	
0.12 in	149	°F	

**Polyflam RPP 2000S R9016 WHI87235**  
**LyondellBasell Industries - Polypropylene Homopolymer**

<b>Electrical</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	V	IEC 60112
<b>Flammability</b>	<b>Nominal Value</b>	<b>Unit</b>	<b>Test Method</b>
Burning Rate <sup>2</sup>			
0.0787 in	0.0	in/min	ISO 3795
0.0787 in	0.0	in/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.03 in	V-2		
0.06 in	V-2		
0.13 in	V-2		
Glow Wire Flammability Index			IEC 60695-2-12
0.030 in	1760	°F	
0.06 in	1760	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.030 in	1610	°F	
0.06 in	1560	°F	
0.12 in	1470	°F	
Oxygen Index	26	%	ISO 4589-2

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Processing (Melt) Temp	356 to 410	°F
Mold Temperature	104 to 176	°F

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Self-Extinguishing