

Polyflam RPP 3225 CS1 BLK

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

25% glass fibre reinforced flame retardant PP homo polymer compound; without PBDE

General

Filler / Reinforcement	• Glass Fiber, 25% Filler by Weight
Additive	• Copper Stabilizer • Flame Retardant
Features	• Copper Contact Stabilized • High Strength • Flame Retardant • Homopolymer
Processing Method	• Injection Molding
Resin ID	• PP GF25 FR(17)

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.48	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	5.0	cm ³ /10min	ISO 1133
Water Absorption (Equilibrium, 73°F, 50% RH)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.15E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	12000	psi	ISO 527-2/1A/5
Tensile Strain (Break)	3.0	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	4.3	ft·lb/in ²	
73°F	4.8	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	19	ft·lb/in ²	
73°F	19	ft·lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	315	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	293	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	264	°F	ISO 306/B50
--	322	°F	ISO 306/A50
Ball Pressure Test (293°F)	Pass		IEC 60695-10-2
RTI Elec			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	
RTI Imp			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	

Polyflam RPP 3225 CS1 BLK

LyondellBasell Industries - Polypropylene Homopolymer

Thermal	Nominal Value	Unit	Test Method
RTI Str			UL 746B
0.06 in	149	°F	
0.12 in	149	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ²			ISO 3795
0.0591 in	0.0	in/min	
0.118 in	0.0	in/min	
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		
Flammability Classification			IEC 60695-11-10, -20
0.06 in	V-0		
0.12 in	V-0		
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in	1760	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in	1290	°F	
0.12 in	1430	°F	
Oxygen Index	28	%	ISO 4589-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	356	°F
Middle Temperature	392	°F
Front Temperature	410	°F
Nozzle Temperature	428	°F
Processing (Melt) Temp	356 to 428	°F
Mold Temperature	104 to 176	°F
Injection Pressure	11600 to 17400	psi
Injection Rate	Slow-Moderate	
Holding Pressure	5800 to 13100	psi
Back Pressure	725 to 1450	psi
Screw Speed	< 709	in/min
Cushion	< 0.197	in

Notes

¹ Typical properties: these are not to be construed as specifications.

² Self-Extinguishing