

Polyflam RPP 3000 SF GRY60535

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

Flame retardant polypropylene homopolymer compound with high flowability

General

Additive	• Flame Retardant
Features	• Flame Retardant • Halogenated • Homopolymer
Processing Method	• Injection Molding

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.00	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	20	cm ³ /10min	ISO 1133
Water Absorption (Equilibrium, 73°F, 50% RH)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	218000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	4500	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	9.0	%	ISO 527-2/1A/50
Flexural Modulus (73°F)	225000	psi	ISO 178
Flexural Stress	5800	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	0.95	ft-lb/in ²	
73°F	1.4	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	6.7	ft-lb/in ²	
73°F	No Break		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	192	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	122	°F	ISO 75-2/af
Vicat Softening Temperature			
--	172	°F	ISO 306/B50
--	306	°F	ISO 306/A120
Ball Pressure Test (275°F)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flammability Classification (0.06 in)	V-0		IEC 60695-11-10, -20
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in	1760	°F	
0.12 in	1760	°F	

Polyflam RPP 3000 SF GRY60535
LyondellBasell Industries - Polypropylene Homopolymer

Flammability	Nominal Value	Unit	Test Method
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in	1340	°F	
0.12 in	1340	°F	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	356	°F
Middle Temperature	392	°F
Front Temperature	410	°F
Nozzle Temperature	428	°F
Processing (Melt) Temp	356 to 428	°F
Mold Temperature	104 to 176	°F
Injection Pressure	11600 to 17400	psi
Injection Rate	Slow-Moderate	
Holding Pressure	5800 to 13100	psi
Back Pressure	725 to 1450	psi
Screw Speed	< 709	in/min
Cushion	< 0.197	in