

Polyflam RPP 374 ND CS1 5V WHI81700

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

20% talc filled flame-retardant PP-Homopolymer

General

Filler / Reinforcement	• Talc, 20% Filler by Weight
Additive	• Copper Stabilizer • Flame Retardant
Features	• Copper Contact Stabilized • Flame Retardant • Homopolymer
Processing Method	• Injection Molding
Resin ID	• PP TD20 FR(17)

Properties¹

Physical	Nominal Value	Unit	Test Method
Density	1.45	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	5.0	cm ³ /10min	ISO 1133
Water Absorption (Equilibrium, 73°F, 50% RH)	0.16	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	537000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	3920	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	2.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	0.86	ft-lb/in ²	
73°F	0.95	ft-lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	5.7	ft-lb/in ²	
73°F	5.7	ft-lb/in ²	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	244	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	176	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	198	°F	ISO 306/B50
--	311	°F	ISO 306/A50
Ball Pressure Test (257°F)	Pass		IEC 60695-10-2
RTI Elec			UL 746B
0.06 in	221	°F	
0.07 in	221	°F	
0.12 in	221	°F	
RTI Imp			UL 746B
0.06 in	221	°F	
0.07 in	221	°F	
0.12 in	221	°F	

Polyflam RPP 374 ND CS1 5V WHI81700
LyondellBasell Industries - Polypropylene Homopolymer

Thermal	Nominal Value	Unit	Test Method
RTI Str			UL 746B
0.06 in	221	°F	
0.07 in	221	°F	
0.12 in	221	°F	
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Comparative Tracking Index	600	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Burning Rate ²			
0.0787 in	0.0	in/min	FMVSS 302
0.0787 in	0.0	in/min	ISO 3795
Flame Rating			UL 94
0.06 in	V-0		
0.12 in	V-0		
0.07 in	5VA		
Flammability Classification			IEC 60695-11-10, -20
0.06 in	V-0		
0.12 in	V-0		
0.07 in	5VA		
Glow Wire Flammability Index			IEC 60695-2-12
0.06 in	1760	°F	
0.07 in	1760	°F	
0.12 in	1760	°F	
Glow Wire Ignition Temperature			IEC 60695-2-13
0.06 in	1380	°F	
0.07 in	1380	°F	
0.12 in	1380	°F	
Oxygen Index	29	%	ISO 4589-2

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	158 to 176	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	356 to 390	°F
Middle Temperature	356 to 410	°F
Front Temperature	356 to 410	°F
Nozzle Temperature	356 to 428	°F
Processing (Melt) Temp	356 to 428	°F
Mold Temperature	100 to 160	°F
Injection Pressure	11600 to 17400	psi
Holding Pressure	5800 to 13100	psi
Back Pressure	< 99.9	psi
Cushion	< 0.197	in

Notes

¹ Typical properties: these are not to be construed as specifications.

² Self-Extinguishing