

Polyfort AQUALOY 125 W14WHI

LyondellBasell Industries - Polypropylene

General Information

Product Description

Aqualoy 125 is 20% Glass-Reinforced Chemically Coupled Polypropylene

General

Filler / Reinforcement	• Glass Fiber, 20% Filler by Weight
Features	• Chemically Coupled
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.03		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	5.6	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Break)	10500	psi	ASTM D638
Flexural Modulus	629000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.8	ft-lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	324	°F	ASTM D648