



Polyfort AFP 3318 GRY 68890

LyondellBasell Industries - Polypropylene Copolymer

General Information

Product Description

High impact PP copolymer, talc filled

General

Features	• Copolymer	• High Impact Resistance
Processing Method	• Injection Molding	

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.08	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	8.0	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	232000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	2900	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft·lb/in ²	
73°F	11	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	21	ft·lb/in ²	
73°F	No Break		
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	6090	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	190	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	122	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	133	°F	ISO 306/B50
--	277	°F	ISO 306/A120
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate			
0.0787 in	< 3.9	in/min	ISO 3795
0.0787 in	< 3.9	in/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in	HB		
0.12 in	HB		

Polyfort AFP 3318 GRY 68890

LyondellBasell Industries - Polypropylene Copolymer

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F