



Polyfort APP30GM06NA-NA GAPEXNAT

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

Gapex APP30GM06NA is a 30% Glass & Talc Filled, UV Stabilized, Impact-Modified Polypropylene

General

Filler / Reinforcement	• Glass Fiber/Talc, 30% Filler by Weight
Features	• Homopolymer
Appearance	• Natural Color
Forms	• Pellets

Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	8.7	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	6380	psi	ASTM D638
Flexural Modulus - Tangent (73°F)	529000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	1.7	ft-lb/in	ASTM D256