

Polyfort FPP 20GFC BLK

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

20% chemical coupled glass fiber reinforced PP-Homopolymer

General

| | |
|------------------------|-------------------------------------|
| Filler / Reinforcement | • Glass Fiber, 20% Filler by Weight |
| Features | • Chemically Coupled • Homopolymer |
| Processing Method | • Injection Molding |

Properties ¹

| Physical | Nominal Value | Unit | Test Method |
|--|---------------|------------------------|----------------------|
| Density | 1.05 | g/cm ³ | ISO 1183/A |
| Melt Volume-Flow Rate (MVR) (230°C/2.16 kg) | 5.0 | cm ³ /10min | ISO 1133 |
| Mechanical | Nominal Value | Unit | Test Method |
| Tensile Modulus | 667000 | psi | ISO 527-1/1A/1 |
| Tensile Stress (Break) | 9860 | psi | ISO 527-2/1A/5 |
| Tensile Strain (Break) | 3.0 | % | ISO 527-2/1A/5 |
| Impact | Nominal Value | Unit | Test Method |
| Charpy Notched Impact Strength | | | ISO 179/1eA |
| -22°F | 3.3 | ft-lb/in ² | |
| 73°F | 3.8 | ft-lb/in ² | |
| Charpy Unnotched Impact Strength | | | ISO 179/1eU |
| -22°F | 12 | ft-lb/in ² | |
| 73°F | 19 | ft-lb/in ² | |
| Hardness | Nominal Value | Unit | Test Method |
| Ball Indentation Hardness | 14500 | psi | ISO 2039-1 |
| Thermal | Nominal Value | Unit | Test Method |
| Deflection Temperature Under Load (66 psi, Unannealed) | 307 | °F | ISO 75-2/Bf |
| Deflection Temperature Under Load 264 psi, Unannealed | 277 | °F | ISO 75-2/Af |
| Vicat Softening Temperature | | | |
| -- | 239 | °F | ISO 306/B50 |
| -- | 320 | °F | ISO 306/A50 |
| Ball Pressure Test (266°F) | Pass | | IEC 60695-10-2 |
| Electrical | Nominal Value | Unit | Test Method |
| Surface Resistivity | > 1.0E+15 | ohms | IEC 60093 |
| Volume Resistivity | > 1.0E+13 | ohms·m | IEC 62631-3-1 |
| Flammability | Nominal Value | Unit | Test Method |
| Burning Rate | | | |
| 0.0787 in | < 3.9 | in/min | ISO 3795 |
| 0.0787 in | < 3.9 | in/min | FMVSS 302 |
| Flammability Classification | | | IEC 60695-11-10, -20 |
| 0.06 in | HB | | |
| 0.12 in | HB | | |

Polyfort FPP 20GFC BLK

LyondellBasell Industries - Polypropylene Homopolymer

Processing Information

| Injection | Nominal Value | Unit |
|------------------------|---------------|------|
| Drying Temperature | 176 | °F |
| Drying Time | 2.0 to 3.0 | hr |
| Processing (Melt) Temp | 428 to 500 | °F |
| Mold Temperature | 86 to 140 | °F |
| Injection Rate | Moderate-Fast | |