

# Polyfort FPP 3790-019 BEI

LyondellBasell Industries - Polypropylene

## General Information

### Product Description

PP compound with 40% talc filler. Long term heat stabilized.

### General

Filler / Reinforcement • Talc, 40% Filler by Weight  
 Processing Method • Injection Molding

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.25	g/cm <sup>3</sup>	ISO 1183
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	11	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	653000	psi	ISO 527-1
Tensile Stress (Break)	3630	psi	ISO 527-2
Tensile Strain (Break)	3.8	%	ISO 527-2
Flexural Modulus	725000	psi	ISO 178
Flexural Stress (7.0% Strain)	2900	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
-22°F	0.81	ft·lb/in <sup>2</sup>	
73°F	1.1	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
-22°F	4.8	ft·lb/in <sup>2</sup>	
73°F	7.1	ft·lb/in <sup>2</sup>	
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	266	°F	ISO 75-2/B
Deflection Temperature Under Load 264 psi, Unannealed	165	°F	ISO 75-2/A
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 62631-3-2
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate (0.0787 in)	2.0	in/min	ISO 3795
Flammability Classification			IEC 60695-11-10, -20
0.03 in	HB		
0.06 in	HB		

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F
Injection Rate	Moderate-Fast	