

Polyfort FPP 22 T LE K1684 BLK71625

LyondellBasell Industries - Polypropylene Homopolymer

General Information

Product Description

22% talc filled and head stabilized PP-Homopolymer with low emission, especially designed for Automotive interior applications

General

Filler / Reinforcement	• Mineral, 22% Filler by Weight
Additive	• Heat Stabilizer
Features	• Heat Stabilized • Low Emissions
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.06	g/cm ³	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	12	cm ³ /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	377000	psi	ISO 527-1/1A/1
Tensile Stress (Yield)	4350	psi	ISO 527-2/1A/50
Tensile Strain (Yield)	6.0	%	ISO 527-2/1A/50
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	0.71	ft·lb/in ²	
73°F	1.4	ft·lb/in ²	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	7.1	ft·lb/in ²	
73°F	19	ft·lb/in ²	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	10900	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	248	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	158	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	201	°F	ISO 306/B50
--	304	°F	ISO 306/A50
Ball Pressure Test (257°F)	Pass		IEC 60695-10-2
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate			
0.0787 in	< 3.9	in/min	ISO 3795
0.0787 in	< 3.9	in/min	FMVSS 302

Polyfort FPP 22 T LE K1684 BLK71625
LyondellBasell Industries - Polypropylene Homopolymer

Flammability	Nominal Value	Unit	Test Method
Flammability Classification			IEC 60695-11-10, -20
0.06 in		HB	
0.12 in		HB	

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F
Injection Rate	Moderate-Fast	