

# Polyfort FPP 40 GFC BLK

LyondellBasell Industries - Polypropylene Homopolymer

## General Information

### Product Description

40 % glass fibre reinforced PP-Homopolymer, chemically coupled

### General

Filler / Reinforcement	• Glass Fiber, 40% Filler by Weight
Features	• Chemically Coupled • Homopolymer
Processing Method	• Injection Molding
Resin ID	• PP-GF

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density	1.21	g/cm <sup>3</sup>	ISO 1183/A
Melt Volume-Flow Rate (MVR) (230°C/2.16 kg)	4.0	cm <sup>3</sup> /10min	ISO 1133
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus	1.17E+6	psi	ISO 527-1/1A/1
Tensile Stress (Break)	13100	psi	ISO 527-2/1A/5
Tensile Strain (Break)	2.7	%	ISO 527-2/1A/5
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179/1eA
-22°F	2.9	ft·lb/in <sup>2</sup>	
73°F	4.8	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179/1eU
-22°F	19	ft·lb/in <sup>2</sup>	
73°F	21	ft·lb/in <sup>2</sup>	
Hardness	Nominal Value	Unit	Test Method
Ball Indentation Hardness (H 358/30)	20900	psi	ISO 2039-1
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	318	°F	ISO 75-2/Bf
Deflection Temperature Under Load 264 psi, Unannealed	297	°F	ISO 75-2/Af
Vicat Softening Temperature			
--	273	°F	ISO 306/B50
--	329	°F	ISO 306/A50
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	> 1.0E+15	ohms	IEC 60093
Volume Resistivity	> 1.0E+13	ohms·m	IEC 62631-3-1
Flammability	Nominal Value	Unit	Test Method
Burning Rate			
0.0787 in	< 3.9	in/min	ISO 3795
0.0787 in	< 3.9	in/min	FMVSS 302
Flammability Classification			IEC 60695-11-10, -20
0.06 in		HB	
0.12 in		HB	

## Polyfort FPP 40 GFC BLK

LyondellBasell Industries - Polypropylene Homopolymer

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F
Injection Rate	Moderate-Fast	