

Polyfort FPP2B05CCBKBLK

LyondellBasell Industries - Polypropylene

General Information

Product Description

FPP2B05CC is a 5% Glass-Reinforced, Chemically-Coupled Polypropylene

General

Filler / Reinforcement	• Glass Fiber, 5.0% Filler by Weight
Features	• Chemically Coupled
Appearance	• Colors Available
Forms	• Pellets
Processing Method	• Injection Molding

Properties ¹

Physical	Nominal Value	Unit	Test Method
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	6.3	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield, 73°F)	5640	psi	ASTM D638
Tensile Elongation (Break)	18	%	ASTM D638
Flexural Modulus	292000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	1.4	ft-lb/in	ASTM D256

Processing Information

Injection	Nominal Value	Unit
Drying Temperature - Desiccant Dryer	160	°F
Drying Time - Desiccant Dryer	2.0 to 4.0	hr
Rear Temperature	390 to 469	°F
Middle Temperature	390 to 469	°F
Front Temperature	390 to 469	°F
Processing (Melt) Temp	390 to 469	°F
Mold Temperature	61 to 151	°F
Injection Rate	Moderate	
Back Pressure	< 50.0	psi
Screw Speed	50 to 150	rpm
Cushion	0.250 to 0.500	in