



# Polyfort FPP30GQ04UL-BK GAPEXBLK

LyondellBasell Industries - Polypropylene

## General Information

### Product Description

Polyfort FPP30GQ04UL-BK GAPEXBLK is a Polypropylene, Unspecified Glass Fiber\Mineral, 31% filled material. Features include: Chemically Coupled, and Impact Modified.

### General

Filler / Reinforcement	• Glass Fiber\Mineral, 31% Filler by Weight
Additive	• Impact Modifier • Impact Modifier
Features	• Chemically Coupled • Impact Modified
Appearance	• Black
Forms	• Pellets

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.15		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	10	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (73°F)	4700	psi	ASTM D638
Tensile Elongation (Break, 73°F)	4.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F	339000	psi	
Tangent : 73°F	357000	psi	
Flexural Strength (73°F)	7700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	0.99	ft·lb/in	ASTM D256
Unnotched Izod Impact (73°F)	3.9	ft·lb/in	ASTM D4812
Gardner Impact (73°F)	5.00	in·lb	ASTM D5420
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	280	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	216	°F	ASTM D648