

# Polyfort GPP-0130QU GY7363GRY

## LyondellBasell Industries - Polypropylene Homopolymer

### General Information

#### Product Description

30% Glass Fiber Reinforced, Chemically Coupled, Homopolymer Polypropylene  
 Melt Flow Adjustable for Application  
 Colors Available  
 Add "U" for UV Stabilized  
 Add "H" for Heat Stabilized

#### General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• Chemically Coupled • Homopolymer
Appearance	• Colors Available
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.14		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	11000	psi	ASTM D638
Tensile Elongation (Break)	4.0	%	ASTM D638
Flexural Modulus	674000	psi	ASTM D790
Flexural Strength	15700	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	1.2	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	286	°F	ASTM D648

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F