

# Polyfort NPP00GD01HB-BKBLK

## LyondellBasell Industries - Polypropylene

### General Information

#### Product Description

Polyfort NPP00GD01HB-BKBLK is a Polypropylene, Unspecified Filler, 0.50% filled material and is typically used in Injection Molding applications. Features include: Impact Modified.

#### General

Filler / Reinforcement	• Filler, 0.50% Filler by Weight
Additive	• Impact Modifier
Features	• Impact Modified
Uses	• Automotive Applications
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.910		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.5	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (73°F)	4210	psi	ASTM D638
Tensile Elongation (Break, 73°F)	150	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F	152000	psi	
Tangent : 73°F	168000	psi	
Flexural Strength (73°F)	5110	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	2.4	ft-lb/in	ASTM D256
Unnotched Izod Impact (73°F)	24	ft-lb/in	ASTM D4812
Gardner Impact (73°F)	285	in-lb	ASTM D3029
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	200	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	120	°F	ASTM D648

### Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F