

# Polyfort RW PP 1407-31 BLACK

LyondellBasell Industries - Polypropylene

## General Information

### Product Description

PP High Impact Unfilled

### General

Features	• High Impact Resistance
Processing Method	• Injection Molding

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	0.912		ASTM D792
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength <sup>2</sup> (Yield)	2900	psi	ASTM D638
Tensile Elongation <sup>2</sup> (Break)	2300	%	ASTM D638
Flexural Modulus <sup>3</sup>	145000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	13	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	167	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	113	°F	ASTM D648

## Processing Information

Injection	Nominal Value	Unit
Drying Temperature	176	°F
Drying Time	2.0 to 3.0	hr
Processing (Melt) Temp	428 to 500	°F
Mold Temperature	86 to 140	°F

### Notes

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> 2.0 in/min

<sup>3</sup> 0.051 in/min