

Polyfort RPP30EU02HB-BK GAPEXBLK

LyondellBasell Industries - Polypropylene Copolymer

General Information

Product Description

Polyfort RPP30EU02HB-BK GAPEXBLK is a Polypropylene Copolymer Glass Fiber, 30% filled material and is typically used in Injection Molding applications. Features include: Chemically Coupled, and Impact Modified.

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Additive	• Impact Modifier
Features	• Chemically Coupled • Impact Modified
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.12		ASTM D792
Melt Mass-Flow Rate (MFR) (230°C/2.16 kg)	7.0	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (73°F)	7110	psi	ASTM D638
Tensile Elongation (Break, 73°F)	6.0	%	ASTM D638
Flexural Modulus			ASTM D790
1% Secant : 73°F	569000	psi	
Tangent : 73°F	582000	psi	
Flexural Strength (73°F)	10800	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (73°F)	4.5	ft-lb/in	ASTM D256
Unnotched Izod Impact (73°F)	16	ft-lb/in	ASTM D4812
Gardner Impact (73°F)	18.0	in-lb	ASTM D5420
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (R-Scale)	91		ASTM D785
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load (66 psi, Unannealed)	309	°F	ASTM D648
Deflection Temperature Under Load 264 psi, Unannealed	280	°F	ASTM D648

Processing Information

Injection	Nominal Value	Unit
Drying Temperature	160 to 180	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	430 to 460	°F
Middle Temperature	441 to 469	°F
Front Temperature	450 to 500	°F
Nozzle Temperature	450 to 500	°F
Processing (Melt) Temp	430 to 460	°F
Mold Temperature	100 to 151	°F

Polyfort RPP30EU02HB-BK GAPEXBLK
LyondellBasell Industries - Polypropylene Copolymer

Injection	Nominal Value	Unit
Injection Rate	Slow-Moderate	
Back Pressure	20.0 to 50.0	psi
Cushion	0.200 to 0.500	in