



# Polyfort TPO-15T BK2030BLK

LyondellBasell Industries - Polyolefin

## General Information

### Product Description

15% Mineral Filled Thermoplastic Polyolefin  
 Melt Flow Adjustable for Application  
 Colors Available  
 Add "U" for UV Stabilized  
 Add "H" for Heat Stabilized

### General

Filler / Reinforcement • Mineral, 15% Filler by Weight

## Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.04		ASTM D792
Melt Mass-Flow Rate (MFR)	18	g/10 min	ASTM D1238
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	3000	psi	ASTM D638
Flexural Modulus	200000	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact	6.9	ft-lb/in	ASTM D256