



TexRes Polypropylene Homopolymer TALC 20

TexCo Resin - Polypropylene Homopolymer

General Information

Product Description

20% Talc Filled, Homopolymer Polypropylene

Melt Flow Adjustable for Application

Colors Available

Add "U" for UV Stabilized

Add "H" for Heat Stabilized

Meets TSM-5601G-9A

General

Filler / Reinforcement	• Talc, 20% Filler by Weight
Features	• Homopolymer
Appearance	• Black • Natural Color

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.05		ASTM D792
Molding Shrinkage - Flow (0.125 in)	0.012	in/in	
Mechanical	Nominal Value	Unit	Test Method
Tensile Strength (Yield)	4800	psi	ASTM D638
Tensile Elongation (Break)	> 10	%	ASTM D638
Flexural Modulus	320000	psi	ASTM D790
Flexural Strength	7400	psi	ASTM D790
Impact	Nominal Value	Unit	Test Method
Notched Izod Impact (0.125 in)	0.50	ft·lb/in	ASTM D256
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	170	°F	ASTM D648
Flammability	Nominal Value	Unit	Test Method
Flame Rating	HB		Internal Method