

DURAFIDE® 6465A6

Polyplastics - Polyphenylene Sulfide

General Information

Product Description

GF and Mineral Reinforced

Low Warpage, Higher Gloss

General

Filler / Reinforcement	• Glass Bead\Glass Fiber, 65% Filler by Weight
Features	• High Gloss • Low Warpage
UL File Number	• E109088
Forms	• Pellets
Part Marking Code (ISO 11469)	• >PPS-(GF+GB)65<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.95	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.030	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	18900	psi	ISO 527-2
Tensile Strain (Break)	0.90	%	ISO 527-2
Flexural Modulus	3.12E+6	psi	ISO 178
Flexural Stress	31200	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	2.9	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	105		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	518	°F	ISO 75-2/A
CLTE - Flow	5.6E-6	in/in/°F	Internal Method
CLTE - Transverse	1.7E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	2.0E+15	ohms·cm	IEC 60093
Electric Strength (0.118 in)	380	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
1 kHz	4.80		
1 MHz	4.80		
Dissipation Factor			IEC 60250
1 kHz	2.0E-3		
1 MHz	2.0E-3		
Arc Resistance	170	sec	ASTM D495
Comparative Tracking Index	175	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating	V-0		UL 94

DURAFIDE® 6465A6
Polyplastics - Polyphenylene Sulfide

Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (590°F, 1000 sec ⁻¹)	320000	mPa·s	ISO 11443
Additional Information	Nominal Value	Unit	
Color Number	HD9050		