

DURAFIDE® 1130T6

Polyplastics - Polyphenylene Sulfide

General Information

Product Description

Special

High Impact

General

Filler / Reinforcement	• Glass Fiber, 30% Filler by Weight
Features	• High Impact Resistance
UL File Number	• E109088
Forms	• Pellets
Part Marking Code (ISO 11469)	• >PPS-I-GF30<

Properties ¹

Physical	Nominal Value	Unit	Test Method
Density	1.52	g/cm ³	ISO 1183
Water Absorption (24 hr, 73°F, 0.0394 in)	0.060	%	ISO 62
Mechanical	Nominal Value	Unit	Test Method
Tensile Stress	22500	psi	ISO 527-2
Tensile Strain (Break)	2.3	%	ISO 527-2
Flexural Modulus	1.45E+6	psi	ISO 178
Flexural Stress	33400	psi	ISO 178
Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength (73°F)	5.7	ft-lb/in ²	ISO 179/1eA
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness (M-Scale)	85		ISO 2039-2
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load 264 psi, Unannealed	491	°F	ISO 75-2/A
CLTE - Flow	1.1E-5	in/in/°F	Internal Method
CLTE - Transverse	2.2E-5	in/in/°F	Internal Method
Electrical	Nominal Value	Unit	Test Method
Volume Resistivity	8.0E+15	ohms·cm	IEC 60093
Electric Strength (0.118 in)	460	V/mil	IEC 60243-1
Relative Permittivity			IEC 60250
1 kHz	3.90		
1 MHz	3.90		
Dissipation Factor			IEC 60250
1 kHz	3.0E-3		
1 MHz	4.0E-3		
Arc Resistance	123	sec	ASTM D495
Comparative Tracking Index	125	V	IEC 60112
Flammability	Nominal Value	Unit	Test Method
Flame Rating (0.06 in)	V-0		UL 94

DURAFIDE® 1130T6

Polyplastics - Polyphenylene Sulfide

Fill Analysis	Nominal Value	Unit	Test Method
Melt Viscosity (590°F, 1000 sec ⁻¹)	370000	mPa·s	ISO 11443
Additional Information	Nominal Value	Unit	
Color Number	HD9050		