

# Ryton® R-7-120BL

## Syensqo - Polyphenylene Sulfide

### General Information

#### Product Description

Ryton® R-7-120NA and R-7-120BL glass fiber and mineral filled polyphenylene sulfide compounds provide good strength and low maintenance molding using conventional molding equipment.

#### General

Filler / Reinforcement	• Glass Fiber\Mineral
Features	• Good Strength
Uses	• Automotive Applications
RoHS Compliance	• RoHS Compliant
Appearance	• Black
Forms	• Pellets
Processing Method	• Injection Molding

### Properties <sup>1</sup>

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.99		ASTM D792
Molding Shrinkage			ISO 294-4
Across Flow : 0.126 in	0.40	%	
Flow : 0.126 in	0.20	%	
Water Absorption (24 hr, 73°F)	0.020	%	ASTM D570
Water Absorption (24 hr, 73°F)	0.021	%	ISO 62
Water Absorption (Saturation, 73°F)	0.13	%	Internal Method
Mechanical	Nominal Value	Unit	Test Method
Tensile Modulus			ISO 527-2
--	3.00E+6	psi	
-- <sup>2</sup>	2.84E+6	psi	
Tensile Strength	18000	psi	ASTM D638
Tensile Stress			ISO 527-2
--	19600	psi	
-- <sup>2</sup>	18600	psi	
Tensile Elongation (Break)	0.90	%	ASTM D638
Tensile Strain			ISO 527-2
Break	0.80	%	
Break <sup>2</sup>	1.0	%	
Flexural Modulus	2.80E+6	psi	ASTM D790
Flexural Modulus	2.76E+6	psi	ISO 178
Flexural Strength	30000	psi	ASTM D790
Flexural Stress	30500	psi	ISO 178
Compressive Strength	38400	psi	ASTM D695
Poisson's Ratio	0.36		ISO 527

# Ryton® R-7-120BL

## Syensqo - Polyphenylene Sulfide

Impact	Nominal Value	Unit	Test Method
Charpy Notched Impact Strength			ISO 179
--	2.7	ft·lb/in <sup>2</sup>	
-- <sup>2</sup>	2.7	ft·lb/in <sup>2</sup>	
Charpy Unnotched Impact Strength			ISO 179
--	7.3	ft·lb/in <sup>2</sup>	
-- <sup>2</sup>	7.6	ft·lb/in <sup>2</sup>	
Notched Izod Impact (0.125 in)	1.0	ft·lb/in	ASTM D256
Notched Izod Impact Strength	2.9	ft·lb/in <sup>2</sup>	ISO 180/A
Unnotched Izod Impact (0.125 in)	4.0	ft·lb/in	ASTM D4812
Unnotched Izod Impact Strength	7.1	ft·lb/in <sup>2</sup>	ISO 180
Hardness	Nominal Value	Unit	Test Method
Rockwell Hardness			ASTM D785
M-Scale	101		
R-Scale	118		
Thermal	Nominal Value	Unit	Test Method
Deflection Temperature Under Load			ASTM D648
264 psi, Unannealed	509	°F	
Melting Temperature	536	°F	ISO 11357-3
CLTE - Flow			ASTM E831
-58 to 122°F	8.3E-6	in/in/°F	
212 to 392°F	8.3E-6	in/in/°F	
CLTE - Transverse			ASTM E831
-58 to 122°F	1.7E-5	in/in/°F	
212 to 392°F	3.9E-5	in/in/°F	
Thermal Conductivity	4.1	Btu·in/hr/ft <sup>2</sup> /°F	Internal Method
UL Temperature Rating	428 to 464	°F	UL 746B
Electrical	Nominal Value	Unit	Test Method
Surface Resistivity	1.0E+16	ohms	ASTM D257
Volume Resistivity	1.0E+15	ohms·cm	ASTM D257
Dielectric Strength	400	V/mil	ASTM D149
Dielectric Constant			ASTM D150
77°F, 1 kHz	4.90		
77°F, 1 MHz	4.90		
Dissipation Factor			ASTM D150
77°F, 1 kHz	4.0E-3		
77°F, 1 MHz	2.0E-3		
Arc Resistance	185	sec	ASTM D495
Comparative Tracking Index (CTI)	250	V	UL 746A
Insulation Resistance <sup>3</sup> (194°F)	1.0E+11	ohms	Internal Method
Flammability	Nominal Value	Unit	Test Method
Flame Rating			UL 94
0.031 in	•	V-0	
	•	5VA	
0.06 in	•	V-0	
	•	5VA	
Oxygen Index	61	%	ASTM D2863

**Ryton® R-7-120BL**  
**Syensqo - Polyphenylene Sulfide**

**Processing Information**

<b>Injection</b>	<b>Nominal Value</b>	<b>Unit</b>
Drying Temperature	275 to 302	°F
Drying Time	2.0 to 4.0	hr
Rear Temperature	563 to 599	°F
Middle Temperature	581 to 617	°F
Front Temperature	599 to 653	°F
Nozzle Temperature	581 to 617	°F
Processing (Melt) Temp	608 to 626	°F
Mold Temperature	275 to 302	°F

**Notes**

<sup>1</sup> Typical properties: these are not to be construed as specifications.

<sup>2</sup> Conditioned data is meant to simulate 23°C 50% RH equilibrium values. Conditioning of specimens was achieved per ISO 1110 by exposing specimens for 11 days, 70°C and 62% RH.

<sup>3</sup> 95%RH, 48 hr