



Hoffman PVC V0-08 CLEAR

Hoffman Plastic Compounds Inc. - Flexible Polyvinyl Chloride

General Information

General

Appearance	• Clear/Transparent
Forms	• Pellets

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.25		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	2100	psi	ASTM D412
Tensile Strength (Break)	2900	psi	ASTM D412
Tensile Elongation (Break)	330	%	ASTM D412
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	93		ASTM D2240
Thermal	Nominal Value	Unit	Test Method
Brittleness Temperature	-15.0	°F	ASTM D746

Additional Information

Durometer Hardness, ASTM D2240, Shore A, instantaneous: 93
 Durometer Hardness, ASTM D2240, Shore A, 10 second delay: 88