



Hoffman PVC V0-072x1 CLEAR

Hoffman Plastic Compounds Inc. - Flexible Polyvinyl Chloride

General Information

General

Appearance	• Clear/Transparent
Forms	• Pellets

Properties¹

Physical	Nominal Value	Unit	Test Method
Density / Specific Gravity	1.21		ASTM D792
Elastomers	Nominal Value	Unit	Test Method
Tensile Stress (100% Strain)	1480	psi	ASTM D412
Tensile Strength (Break)	2700	psi	ASTM D412
Tensile Elongation (Break)	370	%	ASTM D412
Tear Strength	360	lbf/in	ASTM D624
Hardness	Nominal Value	Unit	Test Method
Durometer Hardness (Shore A)	84		ASTM D2240

Additional Information

Durometer Hardness, ASTM D2240, Shore A, instantaneous: 84
 Durometer Hardness, ASTM D2240, Shore A, 15 second delay: 79